

CLASSIFICATION OF REACTION TO FIRE PERFORMANCE IN ACCORDANCE WITH EN 13501-1:2007+A1:2009

Classification no.	2019-Efectis-R000553
Sponsor	Avery Dennison Willem Einthovenstraat 11 2342 BH OEGSTGEEST THE NETHERLANDS
Product name	Avery Dennison® MPI 2006 HOP Hi-Tack
Prepared by	Efectis Nederland BV
Notified body no.	1234
Author(s)	C.C.M. Steinhage B.Sc. A.J. lock
Project number	ENL-18-001256
Date of issue	April 2019
Number of pages	5

1. INTRODUCTION

This classification report defines the classification assigned to **Avery Dennison® MPI 2006 HOP Hi-Tack** in accordance with the procedures given in EN 13501-1:2007+A1:2009.

2. DETAILS OF CLASSIFIED PRODUCT

2.1 GENERAL

The product, **Avery Dennison® MPI 2006 HOP Hi-Tack**, will be used for a wide range of applications on flat and slightly curved substrates.

2.2 MANUFACTURER

Avery Dennison Graphics & Reflective Solutions
P.O. Box 28
2300 AA LEIDEN
THE NETHERLANDS

2.3 PRODUCT DESCRIPTION

According to the sponsor the product is composed of:

- Face film: 80 µm, high opacity gloss white polymeric calendered vinyl;
- Adhesive: 40 µm Permanent, grey acrylic based; designed for low-surface energy substrates;
- Backing paper: StaFlat liner, 145 g/m².

The product has a total thickness of approx. 120 µm and a mass per unit area of approx. 155 g/m² (measured on the product).
See also Appendix 'Product data sheet' in the test reports.

3. STANDARDS, REPORTS, RESULTS AND CRITERIA IN SUPPORT OF THIS CLASSIFICATION

3.1 APPLICABLE (PRODUCT) STANDARDS

EN ISO 11925-2:2010	Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test
EN 13823:2010+A1:2014	Reaction to fire tests for building products - Building products, excluding floorings exposed to the thermal attack by a single burning item
EN 13501-1:2007 +A1:2009	Fire classification of construction products and building elements Part 1: Classification using data from reaction to fire tests

3.2 REPORTS

Name of Laboratories	Name of sponsor	Report ref. no.	Test method
Efectis Nederland BV THE NETHERLANDS	Avery Dennison Graphics & Reflective Solutions THE NETHERLANDS	2019-Efectis-R000551 2019-Efectis-R000552	EN ISO 11925-2:2010 EN 13823:2014

3.3 TEST RESULTS

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – maximum	Compliance with parameters
EN ISO 11925-2				
surface flame impingement	Fs ≤150 mm	6	25	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
EN 13823				
	FIGRA _{0.2MJ} [W/s]	3	50	-
	FIGRA _{0.4MJ} [W/s]		0	-
	THR _{600s} [MJ]		0.7	-
	LFS < edge		-	Compliant
	SMOGRA [m ² /s ²]		10.4	-
	TSP _{600s} [m ²]		42	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant

3.4 CLASSIFICATION CRITERIA

Fire classification of construction products and building elements Excluding floorings and linear pipe thermal insulation products			
Classification criteria			
Class	B	C	D
Test method(s)			
EN ISO 11925-2 Exposure = 30 s	F _s ≤ 150 mm within 60 s Ignition of the paper in EN ISO 11925-2 results in a d2 classification.		
EN 13823	FIGRA _{0,2 MJ} ≤ 120 W/s LFS < edge of specimen THR _{600s} ≤ 7.5 MJ	FIGRA _{0,4 MJ} ≤ 250 W/s LFS < edge of specimen THR _{600s} ≤ 15 MJ	FIGRA _{0,4 MJ} ≤ 750 W/s
Additional classification			
Smoke production	s1 = SMOGRA ≤ 30 m ² /s ² and TSP _{600s} ≤ 50 m ² ; s2 = SMOGRA ≤ 180 m ² /s ² and TSP _{600s} ≤ 200 m ² ; s3 = not s1 or s2		
Flaming Droplets/particles	d0 = no flaming droplets/ particles in EN 13823 within 600 s; d1 = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s; d2 = not d0 or d1.		

4. CLASSIFICATION AND FIELD OF APPLICATION

4.1 REFERENCE OF CLASSIFICATION

This classification has been carried out in accordance with clause 11 of EN 13501-1:2007+A1:2009.

4.2 CLASSIFICATION

The product, **Avery Dennison® MPI 2006 HOP Hi-Tack**, in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0

Reaction to fire classification: B – s1, d0

4.3 FIELD OF APPLICATION

This classification is valid for the following product parameters:

Thickness	120 µm
Surface density	Approx. 155 g/m ² (measured on the product)
Other properties	Colour: White

This classification is valid for the following end use applications:

Substrate	Non-combustible (class A1 according to EN 13238:2010)
Air gap	Including air gap
Methods and means of fixing	Glued, using the products adhesive
Joints	Vertically only
Other aspects of end use conditions	Used for a wide range of applications

4.4 DURATION OF THE VALIDITY OF THIS CLASSIFICATION REPORT

There are no limitations in time on the validity of this report.

5. LIMITATIONS

This classification document does not represent type approval or certification of the product.



C.C.M. Steinhage B.Sc.
Project leader reaction to fire



A.J. Lock
Project leader reaction to fire